


WHAT IS CLAIMED IS:

1. A process for the selective trimerization of olefinic compounds under trimerization conditions in the presence of a catalyst system, said process is effected by using a catalyst system comprising:

A) a cyclopentadienyl titanium complex of formula



wherein

Cp is a cyclopentadienyl type ligand, cyclopentadienyl type ligand being substituted, and combination thereof,

B is a bridging group, based on a single atom selected from the groups 13 to 16 inclusive of the Periodic System,

Ar is a aromatic group, substituted aromatic group, and combinations thereof,

R is, independently, hydrogen, a hydrocarbon residue, hydrocarbon being substituted, hydrocarbon containing heteroatoms, or groups R and B are joined together to form a ring,

n is an integer equal to the valency of B minus 2, and

R¹ is a mono-anionic group; and

B) an activator,

wherein said olefinic compounds are selected from a group consisting of C₂-C₂₀ olefines and mixtures of two or more of these olefins.

25

2. The process according to claim 1, wherein said process is effected at a temperature from 20-150°C, at a pressure from 0.2 to 14 MPa, preferably 1.5 to 3 MPa.

30 3. The process according to claim 1, wherein the single atom of B is selected from the group consisting of B, C, N, O, Si, P and S.

4. The process according to claim 1 wherein

B is carbon or silicon;

35 Ar is phenyl, substituted phenyl, an aromatic entity, and combinations thereof;

R¹ is a halogen atom, mono-anionic hydrocarbon residue, mono-anionic hydrocarbon residue containing heteroatoms, and combinations thereof; and

n is 1 or 2, where n is 2, R is a mono-anionic hydrocarbon residue,
mono-anionic hydrocarbon residue containing heteroatoms, and
combinations thereof; and where n is 1, R is a di-anionic
hydrocarbon residue, di-anionic hydrocarbon residue containing
5 heteroatoms, and combinations thereof.

5. The process according to claim 1, wherein Cp is a
cyclopentadienyl type ligand being substituted, besides said B-(R)_n
10 group, with 1 to 8 groups of formula -YR₂R₃R₄ in which Y is C or Si
and R₂, R₃ and R₄ are, independently, H, halogen, lower alkyl, aryl,
lower-alkyl-aryl, aryl-lower alkyl residue, wherein said alkyl and
aryl are independently substituted or not with one or more lower
alkyl residues, said alkyl and aryl residues being independently
15 provided or not with at least one heteroatom, selected from halogen,
nitrogen, oxygen, sulfur and phosphor.

6. The process according to claim 1, wherein said lower alkyl
residues, being the same or different to each other, are linear or
20 branched C₁-C₅ alkyl residues.

7. The process according to claim 1, wherein said aryl group in
the alkylaryl or arylalkyl residue is a phenyl group.

25 8. The process according to claim 4, wherein said halogen is
fluorine or chlorine.

9. The process according to claim 1, wherein
Ar is a phenyl group, substituted or not at the meta-or para-
30 position;
B is based on a carbon atom;
n is 1 or 2, where n is 2, R is, independently, methyl, or ethyl;
and where n is 1, R is =CH₂, or forms when R is C₄H₈ or C₅H₁₀
together with group B a dianionic cyclic group;
35 Cp is C₅H₄ or C₅H₃(SiMe₃), or C₅H₃(CMe₂Ph); and
R¹ is chlorine, methyl, or benzyl.

10. The process according to claim 1, wherein said titanium
complex is supported on a carrier.

11. The process according to claim 1, wherein said activator is methylalumoxane, a salt of a non-coordinating anion, or a Lewis acid capable of abstracting an anion from said transition metal complex.

5

12. The process according to claim 11 wherein the activator is methylalumoxane and the molar ratio of Ti:Al is from 1:100 to 1:1000.

13. The process according to claim 1, wherein said catalyst system further comprises a scavenger.


10

14. The process according to claim 13, wherein said scavenger is selected from the group consisting of *i*-Bu₃Al and (*i*-Bu₂Al)₂O.

15. A catalyst system for the selective trimerization of olefins, said catalyst system comprising:

15

A) a half-sandwich substituted cyclopentadienyl titanium complex of formula



20

wherein

Cp is a cyclopentadienyl type ligand, substituted cyclopentadienyl type ligand, and combinations thereof,

B is a bridging group, based on a single atom selected from the groups 13 to 16 inclusive of the Periodic System,

25

Ar is a aromatic group, substituted aromatic group,

R is, independently, hydrogen, a hydrocarbon residue, substituted hydrocarbon residue, or hydrocarbon containing heteroatoms, or groups R and B are joined together to form a ring,

30

n is an integer equal to the valency of B minus 2, and

R¹ is a mono-anionic group; and

b) an activator.

16. The catalyst system according to claim 15, wherein the single atom of B is selected from the group consisting of B, C, N, O, Si, P and S.

35

17. The catalyst system according to claim 15 wherein B is carbon or silicon;

Ar is phenyl, substituted phenyl or an aromatic entity, and combinations thereof;

R¹ is a halogen atom, mono-anionic hydrocarbon residue, mono-anionic hydrocarbon containing heteroatoms, and combinations thereof; and

5 n is 1 or 2, where n is 2, R is a mono-anionic hydrocarbon residue, mono-anionic hydrocarbon containing heteroatoms, and combinations thereof; and where n is 1, R is a di-anionic hydrocarbon residue, di-anionic hydrocarbon containing heteroatoms, and combinations thereof.

10

18. The catalyst system according to claim 15, wherein Cp is a cyclopentadienyl type ligand being substituted, besides said B-(R)_n group, with 1 to 8 groups of formula -YR₂R₃R₄ in which Y is C or Si and R₂, R₃ and R₄ are, independently, H, halogen, lower alkyl, aryl, 15 lower-alkyl-aryl, aryl-lower alkyl residue, wherein said alkyl and aryl are independently substituted or not with one or more lower alkyl residues, said alkyl and aryl residues being independently provided or not with at least one heteroatom, selected from halogen, nitrogen, oxygen, sulfur and phosphor.

20

19. The catalyst system according to claim 15, wherein said lower alkyl residues, being the same or different to each other, are linear or branched C₁-C₅ alkyl residues.

25

20. The catalyst system according to claim 15, wherein said aryl group in the alkylaryl or arylalkyl residue is a phenyl group.

21. The catalyst system according to claim 17, wherein said halogen is fluorine or chlorine.

30

22. The catalyst system according to claim 15, wherein Ar is a phenyl group, substituted or not at the meta-or para-position;

B is based on a carbon atom;

35 n is 1 or 2, where n is 2, R is, independently, methyl, or ethyl; and where n is 1, R is =CH₂, or forms when R is C₄H₈ or C₅H₁₀

together with group B a dianionic cyclic group;

Cp is C₅H₄ or C₅H₃(SiMe₃), or C₅H₃(CMe₂Ph); and

R¹ is chlorine, methyl, or benzyl.

23. The catalyst system according to claim 15, wherein said titanium complex is supported on a carrier.

5 24. The catalyst system according to claim 15, wherein said activator is methylalumoxane, a salt of a non-coordinating anion, or a Lewis acid capable of abstracting an anion from said transition metal complex.

10 25. The catalyst system according to claim 24, wherein the activator is methylalumoxane and the molar ratio of Ti:Al is from 1:100 to 1:1000.

15 26. The catalyst system according to claim 15, wherein said catalyst system further comprises a scavenger.

27. The catalyst system according to claim 26, wherein said scavenger is selected from the group consisting of *i*-Bu₃Al and (*i*-Bu₂Al)₂O.